



Jul 06

# Cetol Gupa Wood Filler

## Technical Data Sheet

<b>Description:</b>	Fast drying filler / stopper for <u>interior</u> and <u>exterior</u> use. Available in seven "wood" colours, it is recommended for use with clear or coloured Transparent Wood Finishes, Varnishes, etc.
<b>Characteristics:</b>	Nitro-cellulose binder. Fast drying. Good adhesion to bare wood, finishes, varnishes, etc. Good response to sanding.
<b>Use:</b>	As filler / stopper for small nail holes and cracks.
<b>Application:</b>	
Temperature	Between 5°C - 30°C.
Method	By filling knife. Fill slightly 'proud' and allow to dry. Fill large holes in steps, allowing previous fill to set. (Drying time will vary according to thickness of layers.) Rub down with a fine grade silicon carbide paper in the direction of the grain. Remove all dust. Cetol Gupa is normally used on bare wood prior to application of Cetol HLS, Cetol Filter 7 or TS Interior. Alternatively, it may be applied after the first coat of stain but take care to avoid damaging the surrounding surface of woodstain when sanding. After sanding, Cetol Gupa may be treated like wood. In exterior locations, ensure Cetol Gupa is well overcoated with stain or paint.
Thinning	If contents of can harden, add a couple drops of Acetone or Lacquer Brush Thinners.
Drying Time at 20°C	Up to two hours according to thickness of layer. It is possible to apply several layers of Cetol Gupa within the space of one hour.
Flash Point	Approx 4 C. Inflammable
Clean Up Equipment	Acetone
<b>Properties:</b>	
Shelf Life	Keep in a frost free place.
<b>Availability:</b>	
Packaging	150ml & 750ml tins
Colour Range	7 wood tones: Natural, Light Oak, Dark Oak, Mahogany, Merbau, Meranti (Cedar) and Teak.
The following is a guide only to selecting the correct shade of Gupa when applying to bare wood. As timber colour varies, it is advisable to check / match colour on a test area or offcut.	
Natural	Radiata Pine, Douglas Fir, Spruce
Light Oak	Tasmanian Oak (Victorian Ash), Cypress Pine, Tallowwood, Pacific Maple (Meranti), W.R Cedar
Dark Oak	Rosewood, Walnut
Mahogany	Jarrah, Merbau (Kwila)
Meranti (Cedar)	W.R Cedar, Pacific Maple
Merbau	Merbau(Kwila)
Teak	Teak, Rimu

The effectiveness of our systems is based on many years of practical experience and laboratory

research. Nevertheless, we cannot accept, without prior investigation, any liability for the work produced according to these systems as the ultimate result depends on factors beyond our control.

For full application and technical information contact:  
**Tenaru Timber & Finishes Pty Ltd**  
**P O Box 768 Darlinghurst NSW 1300 Australia**  
Tel: 61 2 9360-4500 Fax: 61 2 9360-1924  
E-mail: [sales@tenaru.com.au](mailto:sales@tenaru.com.au)

All recommendations and instructions are made in good faith without accepting liability because conditions of use will be beyond our control.